

MOTIP High temp

Technical Information

Lacquer to treat surfaces, treated and untreated, which are exposed to very high temperatures. The lacquer is resistant to petrol, chemicals and weather influences. Deco Effect Heat Resistant
Lacquer is available in 3 colours, black, silver and dark anthracite
and is heat resistant to 800°C.

Ord.-no: 302401, 302402, 302403, 305024

Quality & properties

Excellent coverage
Fast drying
Heat resistant to 800°C

Physical & chemical data

Efficiency: 0.2398 – 1,25 - 1,75 m²
Surfaces: Treated and untreated surfaces, which are exposed to very high temperatures.
Flash point:

- n.a.
- 23 °C

Content:

- 0.2398
- 0.238
- 100 ML

How to use

The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600).
The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
Apply the heat resistant lacquer in several thin coats. Before applying the next layer, again shake the aerosol.
After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
Allow to dry for one hour at room temperature. Then heat for 30 to 60 minutes (200°C) to harden the paint coat.
During the curing process smoke is generated from the lacquer.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of May 7, 2025 – This release replaces all eventually earlier issued versions.