

MOTIP Crafts Acrylic Lacquer

Technical Information



Decorative lacquer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic. The lacquer has excellent coverage and a lasting colour and lasting gloss. The lacquer is scratch free and wear-resistant and is resistant to chemicals and weather influences. Crafts Spray Lacquer has excellent vertical stability, so hardly any dripping and excellent adhesion.

Ord.-no: 696241, 696242, 696243, 696244, 103489, 103490, 696236, 696237, 696213, 696219, 696220, 103575, 160677, 696206, 696190, 696152, 107986, 103544, 696145, 696138, 103537, 696121, 103506, 696107, 696091, 696083, 696084, 110061, 696059, 696060, 696046, 696022, 695957, 695612

Quality & properties

Excellent coverage
 Lasting colour and lasting gloss
 Scratch free and wear-resistant
 Excellent vertical stability, so hardly any dripping
 Resistant to chemicals and weather influences
 Excellent adhesion

Physical & chemical data

Base: Acrylic resin

Colourname:

- beige
- signal yellow
- light ivory
- rape yellow
- traffic yellow
- melon yellow
- yellow orange
- pastel orange
- flame red
- carmine red
- ruby red
- wine red
- traffic red
- erica violet
- blue lilac
- ultramarine blue
- sapphire blue
- gentian blue
- sky blue
- turquoise blue
- leaves green
- mossy green
- yellow green
- mint green
- silver grey
- light grey
- nut brown
- chocolate brown
- cream white
- deep black
- silver
- pure white

Degree of gloss:

- high gloss, >85
- mat, 10 ±2

Efficiency:

- 400 ML – 1,25 - 1,75 m²
- 400 ML – 1,25 - 1,75 m²

Dust dry: 5 min

Dry to touch: 10 min

Completely dry: 60 min

Overcoatable: 60 min

Surfaces: wood, metal, aluminium, glass, stone and various types of plastic

Minimum Working Temperature: 15 °C

Maximum Working Temperature: 25 °C

Flash point: n.a.
Temperature resistance: 110 °C
Content: 400 ML

How to use

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust, sand the surface and apply a layer of primer. After drying, sand the base layer (grain 600).

The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample.

Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of August 4, 2025 – This release replaces all eventually earlier issued versions.