MOTIP Wheel Paint

Technical Information



Renew and repair steel and other light metal rims and hubcaps of your car with MOTIP Wheel Paint. Wheel Paint is a fast-drying acrylic paint with lasting gloss offering good coverage, excellent adhesion and good surface hardness. It is resistant to petrol, chemicals, the weather and is UV-resistant and non-fading. Wheel Paint is resistant to wear and scratches.

Ord.-no: 04003, 04008, 04010, 04018, 04019, 04007, 900104

Quality & properties

Non-fading and UV-resistant
Fast drying
Good coverage
Resistant to petrol, chemicals and weather influences
Good surface hardness
Lasting gloss
Wear-resistant and scratch free
Excellent adhesion

Physical & chemical data

Base: Special combi resin
Colourname:
- white
- gold
- steelwheel
- black
- silver

Smell: Characteristic
Degree of gloss:
- gloss, >75
- mat, 10 ±2

Efficiency: 500 ML – 4 - 5 m²
Dust dry: 5 - 10 min
Dry to touch: 10 - 20 min
Completely dry: 120 min
Overcoatable: 120 min
Surfaces: Steel and light metal rims and hubcaps.
Minimum Working Temperature: 10 °C
Maximum Working Temperature: 25 °C
Flash point:
- n.a.
- 27 °C

Temperature resistance: 110 °C
Storage stability:
- 10 years
- 5 years

Content:
- 500 ML
- 12 ML

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com

How to use

Before use, carefully read the directions on the packaging and act accordingly.
Pre Treatment: The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MOTIP primer suitable for the surface. After drying, sand the base layer (grain 600).
Treatment: The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 10 to 25°C.
Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.
In order to obtain high gloss, apply a finishing coat of MOTIP acrylic clear coat.
After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as “special refuse”.

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of August 4, 2025 – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com