

## MOTIP Effect Enamel

## Technical Information

Fast drying nitro cellulose lacquer with good filling properties to embellish and repair pottery and enamelled surfaces. Enamel lacquer is resistant to cleaners and is wear resistant and scratch free. Deco Effect Enamel lacquer has good adhesion, good surface hardness and a lasting gloss.

**Ord.-no:** 303203

---

### Quality & properties

Excellent coverage  
Fast drying  
Lasting gloss

---

### Physical & chemical data

Surfaces: Pottery and enamelled surfaces  
Flash point: n.a.  
Content: 400 ML

---

### How to use

The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600).  
The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.  
Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.  
After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).  
Drying time must be at least 24 hours.  
Water resistant after 7 days.  
The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

**As of May 7, 2025** – This release replaces all eventually earlier issued versions.