



PVC ADHESIVE THIXOTROPIC

THIXOTROPIC RIGID PVC CEMENT



PRODUCT DESCRIPTION

Thixotropic rigid PVC cement.

FIELD OF APPLICATION

For joining pipes, sockets and fittings with interference fit and loose fit (gap filling) in pressure and drainage systems. With special pipe brush for quick and easy application. Suitable for diameters ≤ 400 mm. Max. 16 bar (PN 16). Maximal tolerances 0.8 mm diametrical clearance / 0.2 mm press fit. Suitable for e.g. pipe systems conforming to EN 1329, 1452, 1453, 1455 and ISO 15493 (PVC).

PROPERTIES

- Thixotropic
- Gap filling

CERTIFICATES & STANDARDS

Certificates	
	Adhesive for non-pressure thermoplastic piping systems in installations for the transport/disposal/storage of water (EN 14680).
	Adhesive for thermoplastic piping systems for fluids under pressure in installations for the transport/disposal/storage of water (EN 14814).
Standards	
EN 14680	EN 14680: Meets requirements European standard 14680: Adhesive for non-pressure thermoplastic piping systems.
EN 14814	EN 14814: Meets requirements European standard 14814: Adhesive for thermoplastic piping systems for fluids under pressure.

PREPARATION

Working Conditions: Do not use in temperatures $\leq +5^{\circ}\text{C}$.

APPLICATION

Coverage: Indication of the number of joints per 1 L:

Directions for use:

1. Cut pipes square, chamfer edges and deburr. 2. Clean surfaces with Griffon Cleaner and Cleaner Cloth. 3. Apply adhesive rapidly and evenly all around (4-6x) on both surfaces (pipe thickly, socket thinly). 4. Assemble joint immediately. Remove excess adhesive. Do not load the joint mechanically for the first 10 minutes. Close packaging immediately after use.

Stains/residue: Remove adhesive stains with Griffon Cleaner and Cleaner Cloth.

Points of attention: Brush size varies per packaging volume. Use a suitable packaging (brush) for the diameter to be bonded.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



PVC ADHESIVE THIXOTROPIC

THIXOTROPIC RIGID PVC CEMENT

TECHNICAL SPECIFICATIONS

Chemical base:	Solution of PVC in a mixture of solvents
Chemicals resistance:	The chemical resistance of adhesive joints depends on the gap width, drying time, pressure, temperature, type and concentration of medium. The adhesive joint generally has the same chemical resistance as the material itself. Exceptions to this are a small number of very aggressive chemicals such as concentrated inorganic acids, caustic solutions and strong oxidants.
Colour:	Yellow (transparent)
Density approx.:	1.00 g/cm ³
Flash point:	K1 (<21°C)
Temperature resistance:	60 °C
Temperature resistance, peak load:	95 °C
Solid matter approx.:	22 %
Viscosity:	Thixotropic
Viscosity approx.:	1325 mPa·s

STORAGE CONDITIONS

Shelf life: At least 24 months after production.

Stored in unopened packaging between +5°C and +25°C.

Best Before Date (MM/YY): see packaging. Close packaging properly after use and store in a dry, cool, and frost-free location.

Limited shelf life after opening.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.