

## MOTIP Polyester Putty

## Technical Information



Level irregularities like holes in surfaces of steel, aluminium, wood, concrete and polyester on your car with MOTIP 2-component Polyester Putty. Polyester Putty is elastic and very easy to sand. Polyester putty is re-sprayable with all lacquer systems and resistant to chemicals and the weather. MOTIP Polyester Putty can be applied in layers with a thickness up to 2 cm.

**Ord.-no:** 000051, 000098, 000052, 000055

---

### Quality & properties

Very easy to sand  
Elastic  
Re-sprayable with all lacquer systems  
Resistant to chemicals and weather influences  
Excellent adhesion

---

### Physical & chemical data

Base: Polyester resin  
Colourname: grey  
Smell: Characteristic  
Degree of gloss: mat, 10 ±2  
Completely dry: 60 min  
Overcoatable: 60 min  
Sandable after: 30 min  
Surfaces: Steel, aluminium, wood, concrete, polyester  
Minimum Working Temperature: 10 °C  
Maximum Working Temperature: 25 °C  
Flash point: 31 °C  
Potlife: 3-5 min  
Harder percentage: 2.5 %  
Storage stability: 2 years  
Content:

- 250 G
- 500 G
- 1,00 KG
- 2,00 KG

### How to use

Before use, carefully read the directions on the packaging and act accordingly.

Processing temperature 15 – 25°C.

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

Mix the required amount of putty with the harder. Apply in the desired layer thickness. After hardening, sand and when desired apply a fine putty.

The drying time depends on the ambient temperature.

After use, directly clean the tools used. Do not store the surplus material, mixed with harder, in the can.

### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

**As of August 4, 2025** – This release replaces all eventually earlier issued versions.